

MIL-I-43553B Epoxy Marking Ink

Technical Data Sheet (Page 1 of 2)

Description: MIL-I-43553B is an epoxy marking ink specifically formulated for use on metallic or other non-porous surfaces, and printed wiring boards. Type I is a general usage marking ink, and Type II is a non-conductive marking ink. This material is for spray, brush, roller, or silk screen applications.

Physical Properties:

Tack Free:	Within 1 – 1.5 Hours
Standard Cure Time (Room Temp):	7 Days
Accelerated Cure Time (250 Degrees F):	30 Minutes
Shelf Life:	1 Year
POT Life:	7 Hours

SURFACE PREPARATION: Surface to be coated must be clean, dry, and free of all foreign contaminants including grease, oil, dirt, and paint.

APPLICATION & REDUCTION: Mix 6.5 parts of catalyst to 100 parts ink and let sit for an induction period of 30 minutes. After induction period, thinner may be added to achieve desired viscosity. Do not add more than 3-6% by weight for standard applications or 25-40% by volume for spray applications. Recommended cure time is 7 days at room temperature or 175°F for 90 minutes. Variations in cure schedule will affect electrical resistance properties. See Cure schedule for more curing times.

PRECAUTIONS:

Contents are FLAMMABLE.
KEEP OUT OF THE REACH OF CHILDREN.
Do not take internally.
Use with adequate ventilation.
Avoid contact with skin or eyes.
Read Material Safety Data Sheet before use of this product



MIL-I-43553B Epoxy Marking Ink

Technical Data Sheet (Page 2 of 2)

RECOMMENDED CURE



