



Technical Data Sheet

MIL-PRF-22750G

HI-SOLIDS LOW VOC EPOXY COATING

PRODUCT DESCRIPTION: A two-component, hi-solids epoxy coating for spray and brush applications, furnished in a packaged kit and suitable for use under air pollution regulations. Formulated for the protection against solvents and chemicals on interior and exterior surfaces. It is low "VOC" and lead/chromate free. Available in Type I - Low VOC (High Solids); Type II - Low VOC (High Solids) and VOHAPS free; and Type III - Low VOC (High Solids), VOHAPS free, and DTM (Corrosion Inhibiting).

TYPICAL PROPERTIES:

1. **COLORS:** All Fed-Std-595 Colors
2. **SHELF LIFE:** 1 Year from Date of Mfg.
3. **DRYING TIME:**
 - Set-To-Touch - Within 1 Hour
 - Dry Hard - Within 7 Hours
4. **Thinner:** MIL-T-81772B Ty. II
5. **Gloss Values:**
 - Gloss - 90 minimum
 - Semi-Gloss - 15 - 30
 - Camouflage - 5 maximum
6. **VISCOSITY:** (after thinning)
 - #4 Ford Cup - Max 50 seconds (admixed material)
7. **VOLATILE ORGANIC COMPOUNDS:**
 - Max "VOC - 340 grams/liter (2.8 pounds/gallon)

APPLICATION AND REDUCTION: Each of the two components should be thoroughly mixed separately. Component B is then slowly poured into Component A with constant stirring until a three-to-one ratio by volume is achieved. Allow Induction Time of 30-45 Minutes. Reduce the admixed material approximately one pint per gallon with MIL-T-81772B TY. II Thinner to achieve a viscosity of 16-18 seconds in a #4 Ford Cup or for proper atomization. Mix thoroughly and allow to stand one hour before using. Apply a mist coat and allow to dry 30 minutes. Apply a second coat to a total dry film thickness of 1.4 to 1.8 mils. It is normally applied over MIL-PRF-23377.

Fast. Reliable. Accurate. Superior Coatings of America

Address: P.O. Box 409 Clinton, MI 49236 Office Phone: 734-580-2089 Email: sales@superiorsalesdist.com
www.superiorsalesdist.com